

Datasheet

Austenitic stainless steel

Osprey® PANACEA

Osprey® PANACEA is a nickel-free, high-nitrogen austenitic stainless steel.

EN Name

X15 CrMnMoN 17-11-3

AFNOR

X15 Cr Mn Mo N 17 11 3

Powder designed for

Metal Injection Moulding (MIM)

Additive Manufacturing (AM)



Product description

Osprey® PANACEA is a nickel-free, high-nitrogen austenitic stainless steel. This metal powder is manufactured by Inert Gas Atomization (IGA), producing a powder with a spherical morphology which provides good flow characteristics and high packing density. In addition, the powder has a low oxygen content and low impurity levels, resulting in a metallurgically clean product with enhanced mechanical performance.

Chemical composition (nominal), %

Last updated: Apr 10, 2024 10:56 AM CET

Fe	Bal.
Cr	16.5-17.5
Mn	10.5-11.5
Mo	3.0-3.5
Si	0.40-0.80
O	<0.2>
C	≤0.05
P	≤0.04
S	≤0.04
Ni	≤0.10
Other	Co ≤0.05, N 0.15-0.60, Nb ≤0.73

Powder characteristics and morphology

Powder for Additive Manufacturing

Osprey® metal powder for Additive Manufacturing is characterized by a spherical morphology and high packing density, which confer good flow properties. For powder bed processes these are essential when applying fresh powder layers to the bed to ensure uniform and consistent part build.

For blown powder processes, such as Direct Energy Deposition (DED), good flow ensures uniform build rates. Tight control of the particle size distribution also helps ensure good flowability. Low oxygen powders result in clean microstructures and low inclusion levels in the finished parts.

Powder for Metal Injection Moulding (MIM)

Osprey® MIM powder has a spherical morphology, resulting in high packing density. This enables the manufacture of feedstocks with high powder loading, which not only minimizes binder costs but also reduces part shrinkage during debinding and sintering. Spherical powder also has excellent flow characteristics, resulting in reduced tool wear and consistent mould filling.

Osprey® MIM powder's low oxygen content allows better control of carbon and consistency during

sintering. Low oxygen levels, together with high packing density, also facilitate faster sintering.

Particle size distribution

Powder for Additive Manufacturing

Osprey® metal powder for Additive Manufacturing is available in a wide range of particle size distributions that are tailored to the individual Additive Manufacturing systems. They can also be tailored to the particular requirements of the end application, both in terms of mechanical performance and surface finish.

Process technology	Size (µm)
Binder jetting	≤ 16, ≤ 22, ≤ 32, ≤ 38, ≤ 45
Laser - Powder Bed Fusion (L-PBF)	15 to 53 and 10 to 45
Electron beam - Powder Bed Fusion (E-PBF)	45 to 106
Direct Energy Deposition (DED)	53 to 150

Powder for Metal Injection Moulding (MIM)

Osprey® metal powder for Metal Injection Moulding (MIM) is available in a wide range of particle size distributions, from under 5 µm up to 38 µm. The table shows our standard particle size distributions for MIM powders.

Size (µm)	D10 (µm)	D50 (µm)	D90 (µm)
≤ 38	5.5	13.0	31.0
≤ 32	5.0	12.0	29.0
80% ≤ 22	4.5	11.5	27.0
90% ≤ 22	4.0	10.5	22.0
90% ≤ 16	3.5	8.0	16.0

* Particle size measurements performed using a Malvern laser particle size analyzer, typical D10, D50 and D90 provided.

Tailor-made particle size distributions are available on request. Contact us to discuss your specific requirements.

Mechanical properties

Condition	Proof strength	Tensile strength	Elongation	Hardness
	Rp0.2	Rm	A	HV
	MPa	MPa	%	
MIM sintered	690	1090	35	270
Condition	Yield strength	Tensile strength	Elongation, %	Hardness
	Rp0.2	Rm	A	HV
	ksi	ksi	%	Msi
MIM sintered	100.1	158.1	35	270

Physical properties

Density	7.5 g/cm ³ (0.271 lb/in ³)
Porosity	3%
Melting point	Solidus:~1365°C, liquidus: ~1450°C.

Sintering

Osprey® PANACEA has been industrialized for MIM, which has a defined production process including sintering temperature and time profile.

Sintering at atmospheric pressure: 1000mbar 75% N₂/ 25% H₂

Partial pressure sintering: 800mbar 100% N

Typical sintering cycle: 5 K/min to 600 °C, 1 h hold, 600 °C, 5 K/min to 1250 °C, 6 h hold at 1250 °C, then cooling as fast as possible

A post-sintering solution anneal and a rapid cooling (>150°C/min.) based on an inert gas quench is necessary to create an austenitic microstructure (non-magnetic) and avoid surface chromium nitride precipitation.

Testing

All Osprey® metal powders are supplied with a certificate of analysis containing information on the chemical composition and particle size distribution. Information on other powder characteristics is available upon request.

Packaging

A wide range of packaging options is available, from 5kgs plastic bottles to 250kg metal drums.

- 5 kg (11 lbs) Plastic bottles
- 6 kg (13 lbs) Plastic bottles
- 10 kg (22 lbs) Plastic bottles
- 20 kg (44 lbs) Metal cans
- 100 kg (220 lbs) Steel drums
- 150 kg (330 lbs) Steel drums
- 250 kg (551 lbs) Steel drums

All packaging materials are suitable for air, sea and road freight.

Contact us for more information and to discuss your packaging requirements.