

Datasheet Soft magnetic alloys

Osprey<sup>®</sup> Fe50Ni

Osprey® Fe50Ni is a soft-magnetic binary alloy of iron and nickel which has high magnetic permeability, high saturation induction and low coercive force. It is typically used in electronics and automotive applications.

Powder designed for



### **Product description**

Osprey<sup>®</sup> Fe50Ni is a soft-magnetic binary alloy of iron and nickel which has high magnetic permeability, high saturation induction and low coercive force. The alloy is typically used in electronics and automotive applications.

This powder has material properties that achieve typical values and exceed minimum values, according to MPIF Standard 35.

This metal powder is manufactured by Inert Gas Atomization (IGA), producing a powder with a spherical morphology which provides good flow characteristics and high packing density. In addition, the powder has a low oxygen content and low impurity levels, resulting in a metallurgically clean product with enhanced mechanical performance.



# Chemical composition (nominal), %

Last updated: Jul 19, 2023 9:42 AM CET

Fe	Bal.
С	≤0.05
Mn	≤0.5
Si	≤0.5
Cr	≤0.5
S	≤0.03
Р	≤0.03
Ni	50.0

#### Powder characteristics and morphology Powder for Metal Injection Moulding (MIM)

Osprey<sup>®</sup> MIM powder has a spherical morphology, resulting in high packing density. This enables the manufacture of feedstocks with high powder loading, which not only minimizes binder costs but also reduces part shrinkage during debinding and sintering. Spherical powder also has excellent flow characteristics, resulting in reduced tool wear and consistent mould filling.

Osprey<sup>®</sup> MIM powder's low oxygen content allows better control of carbon and consistency during sintering. Low oxygen levels, together with high packing density, also facilitate faster sintering.

## Particle size distribution

#### Powder for Metal Injection Moulding (MIM)

Osprey<sup>®</sup> metal powder for Metal Injection Moulding (MIM) is available in a wide range of particle size distributions, from under 5  $\mu$ m up to 38  $\mu$ m. The table shows our standard particle size distributions for MIM powders.

Size (µm)	D10 (µm)	D50 (µm)	D90 (µm)
≤ 38	5.5	13.0	31.0
≤ 32	5.0	12.0	29.0



80% ≤ 22	4.5	11.5	27.0
90% ≤ 22	4.0	10.5	22.0
90% ≤ 16	3.5	8.0	16.0

\*Particle size measurements performed using a Malvern laser particle size analyzer, typical D10, D50 and D90 provided.

Tailor-made particle size distributions are available on request.Contact us to discuss your specific requirements.

# Testing

All Osprey<sup>®</sup> metal powders are supplied with a certificate of analysis containing information on the chemical composition and particle size distribution. Information on other powder characteristics is available upon request.

## Packaging

A wide range of packaging options is available, from 5kgs plastic bottles to 250kg metal drums.

5 kg (11 lbs) Plastic bottles 6 kg (13 lbs) Plastic bottles 10 kg (22 lbs) Plastic bottles 20 kg (44 lbs) Metal cans 100 kg (220 lbs) Steel drums 150 kg (330 lbs) Steel drums 250 kg (551 lbs) Steel drums All packaging materials are suitable for air, sea and road freight.

Contact us for more information and to discuss your packaging requirements.

Disclaimer: Data and recommendations are provided for information and guidance only, and the performance or suitability of the material for specific applications are not warranted or guaranteed. Continuous development may necessitate changes in technical data without notice. This datasheet is only valid for Sandvik materials. Datasheet updated: Sep 14, 2023 2:39 PM CET (supersedes all previous editions)